

TWO COLOURS



ONE DIRECTION

Polypropylene

TATREN IM 6 56

Impact copolymer for injection moulding

Description

TATREN IM 6 56 is impact copolymer characterised by excellent long term heat stability, stiffness and impact resistance. It contains antistatic agent.

Applications

TATREN IM 6 56 is intended especially for injection moulding of car parts, household appliances, auto battery cases and other technical items where long term heat stability is required.

TATREN IM 6 56 is suitable for food contact. The product complies to Food Contact Regulations.

Properties

	Test method	Unit	Typical value
MFR (230 °C/2,16 kg)	ISO 1133	g/10 min	6,5
Tensile strength at yield *	ISO 527-1,2	MPa	27,5
Tensile elongation at yield *	ISO 527-1,2	%	6,5
Modulus of elasticity in tension *	ISO 527-1,2	MPa	1600
Flexural modulus *	ISO 178	MPa	1500
Izod impact strength (notched, 23 °C) *	ISO 180/1A	kJ/m ²	10
Izod impact strength (notched, -20 °C) *	ISO 180/1A	kJ/m ²	4,5
HDT (0.46 MPa) *	ISO 75-1,2	°C	104
Rockwell hardness *	ISO 2039/2	R scale	90

* Typical properties, not to be used as specification. Average mechanical property values of several measurements carried out on standard injection-moulded test specimens prepared in accordance with ISO 1873-2.

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP



Slovnaft
PETROCHEMICALS



TVK

Processing

TATREN IM 6 56 can be processed on standard injection moulding machines.

Recommended processing temperatures are 190 – 250 °C.

Storage and Handling

Pellets are packed in 25 kg PE-LD bags and transported on shrink-wrapped pallets at eligible load of polymer 1250 or 1375 kg.

If polymer is stored in conditions of high humidity and fluctuating temperatures, then atmospheric moisture can condense inside the packing. If it happened, it is recommended the pellets to be dried before use. During the storage polypropylene should not be exposed to UV radiation. Producer does not take responsibility for any damages caused by adverse storage.

Polymer should be handled and stored away from contact with direct flames and other ignition sources.

Safety

See MSDS.

Recycling

Polypropylene resins are suitable for recycling using modern recycling methods.

In-house production waste should be kept clean to facilitate direct recycling.

Notes

The information provided in this publication has been compiled to the best of our present knowledge. However, in view of the various applications of polypropylene resins and the equipment used, the processing conditions may differ.

The recommendations and data herein are to be construed as informative only and do not relieve users from carrying out their own tests and experiments prior to processing in order to check suitability for a specific use. It is the responsibility of those to whom we supply our products to ensure that any proprietary rights and existing laws and legislation are observed. Our products are under continuous development, therefore we reserve the right to change the information presented in this brochure at our own discretion.

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Sloznaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP



MANUFACTURER

Slovnaft Petrochemicals, s.r.o.
Vlčie hrdlo 4846
824 12 Bratislava
Slovak Republic
Internet: <http://www.slovnaft.sk>
E-mail: info@slovnaft.sk

CUSTOMER SERVICE

Slovnaft Petrochemicals, s.r.o.
Polymer Marketing and Sales
E-mail:
jana.moncekova@petchem.sk
zuzana.kramarova@petchem.sk
Telephone: + 421 2 4055 6836, + 421 2 4055 6941
Fax: + 421 2 5859 9825

SALES ORGANIZATION**Sales Department**

Slovnaft Petrochemicals, s.r.o.
Polymer Marketing and Sales
Vlčie hrdlo 4846
824 12 Bratislava
Slovak Republic
Telephone: + 421 2 5859 7515, +421 2 5859 7682
Fax: + 421 2 5859 7224

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP



Slovnaft
PETROCHEMICALS



TVK

TVK Inter-Chemol GmbH.

Felnerstrasse 5.
D-60322 Frankfurt am Main
Germany
Telephone: +49 69 154 04 12
Fax: +49 69 154 04 41
E-mail: gaboragoston@tvkic.de

TVK Italia S.r.L.

Via P. Teulié 1.
20136 Milano
Italy
Telephone: +39 02 58 30 5523
Fax: +39 02 58 30 3492
E-mail: tvkitaly@energy.it

TVK-France

182, avenue Charles DeGaulle
F-92200 Neuilly-sur-Seine
France
Telephone: +33 14 745 63 60
Fax: +33 14 745 45 10
E-mail: kacsandi@free.fr

TVK UK Ltd.

707 High Road, North Finchley
London N12 0BT
Great-Britain
Telephone: +44-020/8369 5650
Fax: +44-020/8369 5656
E-mail: dios@tvkuk.com

TVK Ukraine

04073 Kiev
pr. Moskovsky, 6
Telephone: +380 44 4683261
Fax: +380 44 4681562
E-mail: office@tvkukraine.eu

TVK Polska Sp.z.o.o.

ul. Wawozowa 23/12
PL-02-796 Warszawa
Poland
Telephone: +48 22 648 17 95
Fax: +48 22 648 67 94
E-mail: tvkpolska@tvkpolska.pl

MOL- Austria Handels GmbH.

Gartenbaupromenade 2/6
A-1010 Wien
Austria
Telephone: +43 1 515 991 120
Fax: +43 1 513 37 55 1120
E-mail: j.hauk@mol-vie.com

MOL GROUP Moscow

Representative Office TVK
RU-115054 Moscow
Kosmodamianskaya Naberezhnaya
D.52 Strojenie 3
Telephone: +7 495 363 39 55
Fax: +7 495 363 39 46
E-mail: jhanko@rus.mol.hu
ikuskova@rus.mol.hu

SC. MOL Romania P.P. SRL

Str. Danielopolu 4-6
ET2 Sector 1 Cod, 014 134
Bucuresti, Romania
Telephone: +40 21 204 85 00
+40 21 204 85 02
Fax: +40 21 232 1059
E-mail: ematei@molromania.ro

March 2008

TIPELIN TIPOLEN TIPPLEN TATREN BRALEN

The joint product portfolio of TVK and Slovnaft Petrochemicals provide infinite opportunities

MEMBERS OF THE MOL GROUP

Slovnaft
PETROCHEMICALS